



Soleo 6011

Geolam[®]
Architectural Eco-Technology

Hybrid Aluminum/WPC Architectural Elements

Datasheet



*Technical information may change without warning.
Please ensure you that you reference our latest as shown on our website at www.geolaminc.com*

Thickness: 1 5/8 in | 40 mm
Width: 2 3/4 in | 70 mm
Section tolerances in mm: + 0.5 / - 2.0

Fire rating:
On request before order

Surfaces finish: Sanded

Profiles fastening and installation:
Check our website www.geolaminc.com

Standard length: 9 ft 10 in | 3.0 m

Or order custom lengths from:
7 ft to 19 ft 8 in | 2.15 m to 6 m

Weight: 0.81 lb/ft | 1.20 kg/m

Secondary moment I_x (cm⁴): 6.39

Secondary moment I_y (cm⁴): 16.47

Section modulus Z_{+x} (cm³): 3.45

Section modulus Z_{-x} (cm³): 3.45

Section modulus Z_{+y} (cm³): 5.16

Section modulus Z_{-y} (cm³): 4.69

Core in anodized aluminum alloy:
A6063S-T5 Serie 6000

Coefficient of Thermal Expansion (20-100°C):
23.4 µm/m/°C

Modulus of Elasticity: 68.9 GPa

Max Tensile Strength: 186 Mpa

Carbon Footprint:
WPC : 1.54 kg CO₂ /Kg
Profile : 9.005 kg CO₂ /Kg

Sanding finish and/or shading may vary between runs

Standard Colors - Minimum 1,600 ft for all colors.



Teak



Moleskin



Rosewood



Ebony


Non-Standard Colors - 90 day lead time - Minimum order 5,000 ft.



Ivory




Blackwood



Bilinga

Custom Colors Available - Minimum order 10,000 ft.

www.geolaminc.com
Toll free: 1-877-627-3530
info@geolaminc.com



Technical specifications, dimensions in mm		Cross section coefficient Z+x (cm ³)		Wood hybrid system WHS	Type 1.0
Weight (kg/ml)	1.2	Cross section coefficient Z-x (cm ³)	3.45	Soleo 6011	
Cross section, secondary moment Ix (cm ⁴)	6.39	Cross section coefficient Z+y (cm ³)	5.16		
Cross section, secondary moment Iy (cm ⁴)	16.47	Cross section coefficient Z-y (cm ³)	4.69		